



## TEST REPORT

Page 1 of 6

REPORT NUMBER: TURT200119310

APPLICANT NAME : Setkim Kimya İnş.Tah.Paz.San.Tic.Ltd.Şti.

ADDRESS: Battalgazi Mah.Aytop Gıda Sit. F 13 Blok Sultanbeyli

İstanbul / TURKEY TEL:0216 669 03 52

Attention : Atakan Tuncel, Elif Estelik

( atakan.tuncel@divortex.com.tr;elif.estelik@divortex.com.tr )

SAMPLE DESCRIPTION: One sample of Metal item - KLIMA FRESH AIR DEODORIZER

APPLE

DATE IN: 15 September ,2020 ( 12:00:00)

DATE OUT: 21 September ,2020

REQUEST. Rohs Directive (EU) 2015/863 amending Annex II to Directive

2011/65/EU

**RESULTS:** See attachment

		CONCLUSION
PART	DESCRIPTION	
Sample 1	Sample	Pass

This report (including any enclosures and attachments) are prepared for the exclusive use of the Customer(s) named in the report and solely for the purpose for which it is provided and on the basis of instructions and information and/or materials supplied by Intertek's Customer. The test results relate only to the specific items tested and are not intended to be a recommendation for any particular course of action. Customer is responsible for acting as it sees fit on the basis of such results. Unless Intertek provide express prior written consent, no part of this report should be reproduced, distributed or communicated to any third party, nor could it be used for PR activities. Intertek do not accept any liability if this report is used for an alternative purpose from which it is intended, nor do Intertek owe any duty of care to any third party in respect of this report. Except where explicitly agreed in writing, all work and services performed is governed by Intertek Standard Terms and Conditions of Service which is available on request or can be obtained at http://www.intertek.com/terms. Testing reports without signature are not valid. The sample has been provided by the customer and the results apply to the sample as received.

Sample information is supplied by the customer. Unless otherwise requested, this laboratory applies shared risk decision rule. Tests marked (\*) in this test report are not included in the TÜRKAK accreditation schedule for this laboratory.



Kubra AKGUN
Customer Care Executive

An

Zeynep AKIN
Chemical Laboratory Manager

Intertek Test Hizmetleri A.S.

Merkez Mahallesi Sanayi Cad. No.23 Altindag Plaza Yenibosna-34197 /ISTANBUL

Phone: +90 212 496 46 46 Fax: +90 212 452 80 55

e-mail: intertekcg.turkiye@intertek.com http://www.intertek-turkey.com

200119310





REPORT : TURT200119310 Page 2 of 6

## (A) TEST RESULT SUMMARY ACCORDING TO IEC 62321 Electrotechnical Products-Determination of Levels of Six Regulated Substances

TESTING ITEM	RESULT
	Sample 1
Cadmium (Cd) Content	ND
Chromium VI (Cr+6) Content (ppm) (for non- metal)	NA
Chromium VI (Cr+6) Content (µg/cm²) (for metal)	ND
Lead (Pb) Content	ND
Mercury (Hg) Content	ND
Flame Retardants	
Polybrominated Biphenyls (PBB)	NA
Monobromobiphenyl (MonoBB)	NA
Dibromobiphenyl (DiBB)	NA
Tribromobiphenyl (TriBB)	NA
Tetrabromobiphenyl (TetraBB)	NA
Pentabromobiphenyl (PentaBB)	NA
Hexabromobiphenyl (HexaBB)	NA
Heptabromobiphenyl (HeptaBB)	NA
Octabromobiphenyl (OctaBB)	NA
Nonabromobiphenyl (NonaBB)	NA
Decabromobiphenyl (DecaBB)	NA
Polybrominated Diphenyl Ethers (PBDE)	NA
Monobromodiphenyl Ether (MonoBDE)	NA
Dibromodiphenyl Ether (DiBDE)	NA
Tribromodiphenyl Ether (TriBDE)	NA
Tetrabromodiphenyl Ether (TetraBDE)	NA
Pentabromodiphenyl Ether (PentaBDE)	NA
Hexabromodiphenyl Ether (HexaBDE)	NA
Heptabromodiphenyl Ether (HeptaBDE)	NA
Octabromodiphenyl Ether (OctaBDE)	NA
Nonabromodiphenyl Ether (NonaBDE)	NA
Decabromodiphenyl Ether (DecaBDE)	NA
Phthalates	

Remarks :ppm=Parts per million based on dry weight of sample  $\mu g/cm^2=Microgram$  per square centimetre mg/kg with 50 cm²=Milligram per kilogram with 50 square centimetre ND =Not detected NA =Not applicable NR =Not requested





REPORT : TURT200119310 Page 3 of 6

TESTING ITEM	RESULT
	Sample 1
Dibutyl phthalate (DBP) (84-74-2)	NA
Di(2-ethylhexyl) phthalate (DEHP)(117-81-7)	NA
Benzyl butyl phthalate (BBP) (85-68-7)	NA
Diisobutyl Phthalate (DIBP) (84-69-5)	NA

Remarks :ppm=Parts per million based on dry weight of sample  $\mu g/cm^2 = Microgram$  per square centimetre mg/kg with 50 cm²=Milligram per kilogram with 50 square centimetre ND =Not detected NA =Not applicable NR =Not requested





REPORT : TURT200119310 Page 4 of 6

(B) REQUIREMENT:

SUBSTANCE	LIMITS		
Cadmium (Cd) Content	0.01 % (100 ppm)		
Chromium VI (Cr+6) Content (ppm) (for non metal)	0.1 % (1000 ppm)		
Chromium VI	<u>Colorimetric</u> <u>result</u>	Qualitative Result	
(Cr+6) Content (µg/cm²) (for metal)	< 0.10 μg/cm <sup>2</sup> ≥ 0.10 μg/cm <sup>2</sup> and ≤ 0.13 μg/cm <sup>2</sup> > 0.13 μg/cm <sup>2</sup>	Negative Inconclusive Positive	
Lead (Pb) Content	0.1 % (1000 ppm)		
Mercury (Hg) Content	0.1 % (1000 ppm)		
Flame Retardants	0.1 % (1000 ppm)		
Dibutyl Phthalate (DBP)	0.1 % (1000 ppm)		
Diethyl Hexyl Phthalate (DEHP)	0.1 % (1000 ppm)		
Benzyl Butyl Phthalate (BBP)	0.1 % (1000 ppm)		
Diisobutyl Phthalate (DIBP)	0.1 % (1000 ppm)		





REPORT : TURT200119310 Page 5 of 6

## (C) TEST METHOD :

Testing Item	Testing Method	Reporting Limit
Cadmium (Cd)Content	With reference to IEC 62321-5:2013,by microwave or acid digestion and determined by ICP-OES	Plastic : 2.5 ppm, Metal : 5 ppm, Ceramic : 1.25 ppm
Lead (Pb)Content	With reference to IEC 62321-5:2013,by microwave or acid digestion and determined by ICP-OES	Plastic : 5 ppm, Metal : 10 ppm, Ceramic : 2.5 ppm
Mercury (Hg)Content	With reference to IEC 62321-4:2017,by microwave or acid digestion and determined by ICP-OES	Plastic : 5 ppm, Metal : 10 ppm, Ceramic : 2.5 ppm
Chromium VI (Cr6+) (For non-metal)	With reference to IEC 62321-7- 2:2017,by alkaline digestion and determined by UV-VIS spectrophotometer	Plastic: 25 ppm (PVC based) /8.33 ppm (other), Ceramic: 8.33 ppm
Chromium VI (Cr6+) (For metal)	With reference to IEC 62321-7- 1:2015 ,by boiling water extraction and determined by UV-VIS spectrophotometer	0.1 mg/kg with 50 cm <sup>2</sup> (IN TESTING SOLUTION)
PBBs/PBDEs	With reference to IEC 62321-6:2015,by solvent extraction and determined by GC/MS and HPLC	5 ppm
Phthalates	With reference to IEC 62321-8 (111/321/CD), by solvent extraction and determined by GC-MS.	50 ppm





21 September ,2020

Page 6 of 6

TEST REPORT
REPORT :TURT200119310

Sample 1

